

PERMACOL 2035E-5

Diedenweg 94
6717 KV EDE
The Netherlands

Tel +31 (0)318 640740
Fax +31 (0)318 635099
E-mail: adhesives@permacol.nl
<http://www.permacol.nl>

DESCRIPTION:

The PERMACOL 2035E-5R is a one component adhesives on epoxy base for SMT purposes. Adhesives of the PERMACOL 2035E-5R can be preferably applied by high speed dispensing. These adhesives hold electronic components in position and prevent movement due to vibration even before curing.

The cured adhesive has excellent electric properties and heat resistance during soldering.

PERMACOL	MAIN APPLICATION
2035E/5R (red)	Universal SMD-adhesive. High dispensing adhesive.

	2035E/5
Green strength	900 Pa.
Viscosity at D=30/s	45 Pa.sec.

It must be clear that the curing time depends on several parameters. Oven capacity, board design, type of components on Printed Circuit Board, and type of Printed Circuit Board (multilayers have higher heat capacity) can influence the cure speed.

SURFACE TEMPERATURE	MINIMUM HEATING TIME
100°C	6 minutes
125°C	2 minutes
150°C	90 seconds

Storage stability:

PERMACOL SMD adhesives is storable at 5-7°C for 6 months in unopened original packaging. Refrigerated adhesives must be allowed to return to room temperature before use. For screen printing adhesives, contamination of the unused material will be avoided if no material is returned to its original packaging.

CLEANING:

At room temperature, the remaining uncured adhesive can be removed and cleaned by means of solvents as Ethanol, Acetone, Isopropylalcohol (IPA), or gamma-Butyrolactone (PC66).

Cured adhesives must be removed mechanically. To avoid damage of components and/or PCB, it is advised to heat up the adhesive or bond over 100°C (over the softening point of the adhesive). At this temperature, the adhesive dot will be soft and the component can easily be removed by means of torsion.

PACKAGING:

The PERMACOL 2035E-5 can be supplied bubble free in all dispenser-specific syringes, tins, pots, and Euro syringe.

HANDLING AND SAFETY PRECAUTIONS:

The PERMACOL 2035E-5R is for industrial purposes only. Read Material Safety Data Sheets (MSDS) prior to using product. Avoid contact with eyes, skin or clothing because this material may cause eye irritation, skin irritation or allergic skin reaction if prolonged or repeated exposure is present, and is harmful if inhaled or swallowed. Wear eye protection and impervious gloves when handling, keep container closed when not in use.

EN – Legal Disclaimer

The products of Permacol (the "Supplier"), are sold subject to the supplier's standard conditions of sale, which are included in applicable sales agreements, printed on the back side of invoices, or available upon request. Although the information, recommendations or advice contained herein is given in good faith, supplier makes no warranty or guarantee, express or implied, (I) that the results described herein will be obtained under end-use conditions, or (II) as to the effectiveness or safety of any design incorporating supplier's products, recommendations or advice. Nothing in this or any other document shall alter, vary, supersede or operate as a waiver of any of the supplier's standard conditions of sale.

Each user bears the full responsibility for making its own determination as to the suitability of Supplier's products, recommendations or advice for its own particular purpose. Each user must identify and perform tests and analyses sufficient to assure it that its finished parts will be safe and suitable for use under end-use conditions. Because actual use of products by the user is beyond the control of Supplier, such use is within the exclusive responsibility of the user, and Supplier cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Further, no statement contained herein concerning a possible or suggested use of any product is intended or should be construed to grant any license under any patent or other intellectual property right of Supplier, or as a recommendation for the use of such material in the infringement of any patent or other intellectual property right.